

Lushan EP252

PE

Guangzhou Lushan New Materials Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength	23	MPa	ASTM D 638
Elongation at Break	800	%	ASTM D 638
Thermal properties			
ASTM Data			
Vicat Temperature	115	°C	ASTM D 1525
Other properties			
Density	940	kg/m ³	ASTM D 792

Characteristics**Features**

Good Adhesion

Regional Availability

Asia Pacific

Chemical Resistance

Oxidation Resistance