

Lushan L-5R(F)

PE

Guangzhou Lushan New Materials Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	6	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	23	MPa	ASTM D 638
Elongation at Break	800	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	134	°C	ASTM D 3418
Vicat Temperature	113	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	945	kg/m ³	ASTM D 792

Characteristics**Processing**

Coating

Delivery form

Powder

Features

Good Adhesion, Copolymer

Chemical Resistance

Oil Resistance

Regional Availability

Asia Pacific