

## Lushan L-5R(HC)

PE

Guangzhou Lushan New Materials Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	3.8	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	26	MPa	ASTM D 638
Elongation at Break	960	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melting Temperature	131	°C	ASTM D 3418
Vicat Temperature	115	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	941	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Coating

#### Delivery form

Granules

#### Features

Good Adhesion, Copolymer

#### Chemical Resistance

Oil Resistance

#### Regional Availability

Asia Pacific