

**MICROLINK XL28**

PE

MICROPOL - Stamford Products Limited

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Stress at break	<b>23</b>	MPa	ISO 527
Strain at break	<b>&gt;50</b>	%	ISO 527
Flexural modulus	<b>750</b>	MPa	ISO 178

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>940</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Rotational Molding

**Delivery form**

Powder

**Special Characteristics**

Flame retardant, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Features**

Crosslinkable, Copolymer

**Chemical Resistance**

General Chemical Resistance, Environmental Stress Crack Resistance

**Regional Availability**

Europe