

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Optical properties	Value	Unit	Test Standard
ASTM Data			
Gloss	85	-	ASTM D 2457
Haze	3	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	938	kg/m ³	ASTM D 792

Characteristics

Processing

Film Extrusion

Special Characteristics

Heat stabilized or stable to heat

Features

Blending Resin, Copolymer, Hexene Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific