

**Novapol® TF-Y534-IP**

PE

Nova Chemicals Corp.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>0.75</b>	g/10min	ASTM D 1238
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Optical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Gloss	<b>63</b>	-	ASTM D 2457
Haze	<b>9</b>	%	ASTM D 1003

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>934</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Film Extrusion

**Additives**

Antiblocking agent

**Features**

Copolymer, Hexene Copolymer

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

Packaging

**Regional Availability**

North America, Europe, Asia Pacific