

Novapol® TF-Y826-D

PE

Nova Chemicals Corp.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.8	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Other properties	Value	Unit	Test Standard
Density	926	kg/m ³	ASTM D 792

Characteristics**Processing**

Film Extrusion

Additives

Antiblocking agent

Features

Copolymer, Hexene Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific