

PL115GN23

PE

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7.5	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Other properties			
Density	950	kg/m ³	ISO 1183
Processing Recommendation Extrusion			
Feed temperature	30 - 50	°C	-
Zone 1	140 - 160	°C	-
Zone 2	160 - 180	°C	-
Zone 3	180 - 200	°C	-

Characteristics**Processing**

Wire/Cable Extrusion

Features

Tribologic Grade

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa