

PL2001NT

PE

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Other properties	Value	Unit	Test Standard
Density	940	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Feed temperature	80 - 100	°C	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Feed temperature	80 - 100	°C	-

Characteristics**Processing**

Injection Molding, Pipe/Tube Extrusion, Sheet Extrusion, Other Extrusion

Delivery form

Natural Color

Features

Tribologic Grade

Certifications

RoHS compliant

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa