

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.6	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	570	MPa	ISO 527
ASTM Data			
Tensile Strength	20	MPa	ASTM D 638
Elongation at Break	350	%	ASTM D 638
Thermal properties			
ASTM Data			
Vicat Temperature	126	°C	ASTM D 1525
Other properties			
Density	940	kg/m ³	ASTM D 792

Characteristics

Processing

Pipe/Tube Extrusion

Regional Availability

North America, Europe, Asia Pacific

Features

Crosslinkable