

Polyethylene LP 390-01

PE

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	22.8	MPa	ASTM D 638
Flexural Modulus	792.9	MPa	ASTM D 790
Shore D Hardness	59	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	953	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Special Characteristics

High impact or impact modified

Delivery form

Natural Color

Regional Availability

North America