

**POLYFLAM® RLP 801**

PE

LyondellBasell Industries

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>10</b>	MPa	ASTM D 638
Elongation at Break	<b>125</b>	%	ASTM D 638
Flexural Modulus	<b>112</b>	MPa	ASTM D 790
Flexural Strength	<b>6</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>264</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>3.02</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1090</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America

**Features**

Blending Resin, Copolymer