

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Izod notched impact strength, +23°C	N	kJ/m ²	ISO 180/1A
Shore A hardness	61	-	ISO 7619-1
Shore D hardness	16	-	ISO 7619-1
ASTM Data			
Tensile Modulus	4	MPa	ASTM D 638
Elongation at Break	800	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	49	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	862	kg/m ³	ISO 1183

Characteristics

Special Characteristics

High impact or impact modified

Features

Blending Resin

Applications

Automotive

Regional Availability

Europe