

Revolve® M-649

PE

Matrix Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Yield stress	16.8	MPa	ISO 527
Flexural modulus, 23°C	940	MPa	ISO 178
Other properties			
Density	1030	kg/m ³	ISO 1183

Characteristics**Processing**

Rotational Molding

Special Characteristics

Flame retardant, U.V. stabilized or stable to weather

Delivery form

Pellets, Powder, Black, Natural Color

Regional Availability

Europe, Asia Pacific