

## Revolve® M-760 Super-Linear

PE

Matrix Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	3.3	g/10min	ISO 1133
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	23.8	MPa	ISO 527
Flexural modulus, 23°C	1510	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	952	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Rotational Molding

#### Delivery form

Powder, Black, Natural Color

#### Special Characteristics

High impact or impact modified

#### Applications

Sports Equipment

#### Regional Availability

Europe, Asia Pacific