

Revolve® N-131 Super-Linear

PE

Matrix Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3.5	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Yield stress	18.7	MPa	ISO 527
Flexural modulus, 23°C	935	MPa	ISO 178
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
Other properties			
Density	945	kg/m ³	ISO 1183

Characteristics

Processing

Rotational Molding

Delivery form

Powder, Black, Natural Color

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Applications

Sports Equipment

Regional Availability

Europe, Asia Pacific