

Revolve® N-261

PE

Matrix Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Yield stress	16	MPa	ISO 527
Flexural modulus, 23°C	650	MPa	ISO 178
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	45	°C	ISO 75-1/-2
Other properties			
Density	935	kg/m ³	ISO 1183

Characteristics**Processing**

Rotational Molding

Special Characteristics

High impact or impact modified

Delivery form

Pellets, Powder, Black, Natural Color

Regional Availability

Europe, Asia Pacific