

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	9.3	MPa	ASTM D 638
Elongation at Break	850	%	ASTM D 638
Tear Strength	39.2	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	868	kg/m ³	ASTM D 792

Characteristics

Features

Copolymer