

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	11.8	MPa	ASTM D 638
Elongation at Break	900	%	ASTM D 638
Tear Strength	41.2	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	880	kg/m ³	ASTM D 792

Characteristics

Features

Copolymer