

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>3.5</b>	g/10min	ASTM D 1238
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Shore A Hardness	<b>89</b>	-	ASTM D 2240
Shore D Hardness	<b>40</b>	-	ASTM D 2240
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	<b>0.5</b>	%	ASTM D 1003
<b>Other properties</b>			
Density	<b>902</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Film Properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Break, MD	<b>50</b>	MPa	ASTM D 882
Tensile Strength at Break, TD	<b>44</b>	MPa	ASTM D 882
Elongation at Break, MD	<b>520</b>	%	ASTM D 882
Elongation at Break, TD	<b>600</b>	%	ASTM D 882

**Characteristics**

**Features**

Copolymer