

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	6	MPa	ASTM D 638
Elongation at Break	1100	%	ASTM D 638
Tear Strength	35.3	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	868	kg/m ³	ASTM D 792

Characteristics

Features

Copolymer