

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------------|---------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 1 | g/10min | ASTM D 1238 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |

| Thermal properties | Value | Unit | Test Standard |
|---------------------|-----------|------|---------------|
| ASTM Data | | | |
| Melting Temperature | 98 | °C | ASTM D 3418 |

| Optical properties | Value | Unit | Test Standard |
|--------------------|------------|------|---------------|
| ASTM Data | | | |
| Haze | 2.7 | % | ASTM D 1003 |

| Other properties | Value | Unit | Test Standard |
|------------------|------------|-------------------|---------------|
| Density | 900 | kg/m ³ | ASTM D 792 |

| Film Properties | Value | Unit | Test Standard |
|-------------------------------|------------|------|---------------|
| ASTM Data | | | |
| Tensile Strength at Break, MD | 50 | MPa | ASTM D 882 |
| Tensile Strength at Break, TD | 55 | MPa | ASTM D 882 |
| Elongation at Break, MD | 620 | % | ASTM D 882 |
| Elongation at Break, TD | 670 | % | ASTM D 882 |

Characteristics

Features

Heat Sealable, Copolymer

Applications

Packaging