

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ASTM Data			
Melting Temperature	96	°C	ASTM D 3418
Optical properties			
ASTM Data			
Haze	0.5	%	ASTM D 1003
Other properties			
Density	900	kg/m ³	ASTM D 792
Film Properties			
ASTM Data			
Tensile Strength at Break, MD	51	MPa	ASTM D 882
Tensile Strength at Break, TD	49	MPa	ASTM D 882
Elongation at Break, MD	490	%	ASTM D 882
Elongation at Break, TD	700	%	ASTM D 882

Characteristics

Features

Heat Sealable, Copolymer, Octene Copolymer

Applications

Packaging