

SABIC® FORTIFY™ C1070

PE

Saudi Basic Industries Corporation (SABIC)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	9.3	MPa	ASTM D 638
Tear Strength	39.2	kN/m	ASTM D 624

Characteristics**Features**

Copolymer