

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	9.3	MPa	ASTM D 638
Shore D Hardness	21	-	ASTM D 2240
Tear Strength	39.2	kN/m	ASTM D 624

Characteristics

Features

Copolymer