

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.1	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Optical properties	Value	Unit	Test Standard
ASTM Data			
Haze	7	%	ASTM D 1003

Film Properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield, MD	11	MPa	ASTM D 882
Tensile Strength at Yield, TD	10	MPa	ASTM D 882
Tensile Strength at Break, MD	51	MPa	ASTM D 882
Tensile Strength at Break, TD	49	MPa	ASTM D 882
Elongation at Break, MD	660	%	ASTM D 882
Elongation at Break, TD	730	%	ASTM D 882

Characteristics

Features

Copolymer