

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.8	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Optical properties	Value	Unit	Test Standard
ASTM Data			
Gloss	61	-	ASTM D 2457
Haze	16.6	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	926	kg/m ³	ASTM D 792

Characteristics

Processing

Film Extrusion

Additives

Antiblocking agent

Features

Heat Sealable, Copolymer, Octene Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific