

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.3	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	190	MPa	ISO 527
Tensile Strength	14	MPa	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	60	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	130	°C	ISO 11357-1/-3
Other properties			
Value			
Density	920	kg/m ³	ISO 1183
Moisture Content	0.1	%	-

Characteristics

Processing

Other Extrusion

Special Characteristics

U.V. stabilized or stable to weather

Delivery form

Natural Color

Regional Availability

Europe