

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Strength	8	MPa	ISO 527
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	130	°C	ISO 11357-1/-3
Vicat softening temperature, B	75	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
<b>Other properties</b>			
Density	910	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding

#### Special Characteristics

U.V. stabilized or stable to weather

#### Delivery form

Black

#### Regional Availability

Europe