

Product Texts

TPSeal® PE FOAM 155 is based on a new generation metallocene Polyethylene with hexene as comonomer.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3.8	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Other properties	Value	Unit	Test Standard
Density	940	kg/m ³	ISO 1183

Characteristics

Processing
Rotational Molding

Applications
Sports Equipment

Delivery form
Powder, Natural Color

Regional Availability
Europe