

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	120	°C	ISO 11357-1/-3
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Glow Wire Flammability Index (GWFI)	850	°C	IEC 60695-2-12

Characteristics

Processing

Rotational Molding

Delivery form

Pellets, Powder, White

Special Characteristics

Flame retardant, Halogen-free

Applications

Building Construction

Regional Availability

Europe