

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>Other Standards<sup>S1</sup></b>			
Melt flow index, MFI	7.6	g/10min	GOST 11645-73

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>Other Standards<sup>S1</sup></b>			
Stress at break	8.8	MPa	GOST 11262-2017
Strain at break	400	%	GOST 11262-2017

S: These properties are reported by the producer according standards that are different to our defaults.

## Characteristics

### Processing

Film Extrusion, Pipe/Tube Extrusion

### Delivery form

Pellets, Natural Color

### Certifications

Food contact

### Applications

Medical, Toys

### Regional Availability

Europe, Asia Pacific