

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Shore D hardness	52	-	ISO 7619-1

Electrical properties	Value	Unit	Test Standard
ISO Data			
Electric strength	22	kV/mm	IEC 60243-1

Processing Recommendation Extrusion	Value	Unit	Test Standard
Zone 1	150	°C	-
Zone 2	170	°C	-
Zone 3	170	°C	-
Zone 4	170	°C	-
Nozzle temperature	170	°C	-

Characteristics

Processing

Wire/Cable Extrusion, Other Extrusion

Delivery form

Natural Color

Features

Crosslinkable, Thermal Stability

Chemical Resistance

Oxidation Resistance

Applications

Electrical and Electronical

Regional Availability

North America