

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|---------|---------------|
| ISO Data | | | |
| Melt flow index, MFI | 1 | g/10min | ISO 1133 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |

| Mechanical properties | Value | Unit | Test Standard |
|-----------------------|-------|------|---------------|
| ISO Data | | | |
| Tensile Strength | 15 | MPa | ISO 527 |
| Strain at break | 300 | % | ISO 527 |
| Shore D hardness | 52 | - | ISO 7619-1 |

| Electrical properties | Value | Unit | Test Standard |
|-----------------------|-------|-------|---------------|
| ISO Data | | | |
| Electric strength | 22 | kV/mm | IEC 60243-1 |

| Processing Recommendation Extrusion | Value | Unit | Test Standard |
|-------------------------------------|-------|------|---------------|
| Zone 1 | 150 | °C | - |
| Zone 2 | 170 | °C | - |
| Zone 3 | 170 | °C | - |
| Zone 4 | 170 | °C | - |
| Nozzle temperature | 170 | °C | - |

Characteristics

- Processing**
Wire/Cable Extrusion, Other Extrusion
- Delivery form**
Natural Color
- Additives**
Metal deactivator
- Features**
Crosslinkable, Thermal Stability

- Chemical Resistance**
Oxidation Resistance
- Applications**
Electrical and Electronical
- Regional Availability**
North America