

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	1	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	15	MPa	ISO 527
Strain at break	300	%	ISO 527

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Electric strength	30	kV/mm	IEC 60243-1

Other properties	Value	Unit	Test Standard
Density	923	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Processing**  
Wire/Cable Extrusion

**Features**  
Crosslinkable, Low Odor

**Applications**  
Electrical and Electronical

**Regional Availability**  
North America, Europe, Asia Pacific, South and Central America, Near East/Africa