

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Shore D hardness	52	-	ISO 7619-1
Electrical properties			
ISO Data			
Electric strength	20	kV/mm	IEC 60243-1
Other properties			
Density	933	kg/m ³	ISO 1183
Processing Recommendation Extrusion			
Zone 1	150	°C	-
Zone 2	170	°C	-
Zone 3	170	°C	-
Zone 4	170	°C	-
Nozzle temperature	170	°C	-

Characteristics

Processing

Wire/Cable Extrusion

Delivery form

Black

Special Characteristics

U.V. stabilized or stable to weather

Features

Crosslinkable

Chemical Resistance

Oxidation Resistance

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa