

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	1	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	20	MPa	ISO 527
Strain at break	300	%	ISO 527
Shore D hardness	55	-	ISO 7619-1

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Electric strength	20	kV/mm	IEC 60243-1

Other properties	Value	Unit	Test Standard
Density	940	kg/m³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Melt temperature	190 - 195	°C	-
Zone 1	150	°C	-
Zone 2	185	°C	-
Zone 3	185	°C	-
Zone 4	185	°C	-
Nozzle temperature	185	°C	-

**Characteristics**

**Processing**

Other Extrusion

**Delivery form**

Black

**Special Characteristics**

U.V. stabilized or stable to weather

**Features**

Crosslinkable, Thermal Stability

**Chemical Resistance**

Oxidation Resistance

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa