

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	9	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	23.5	MPa	ASTM D 638
Elongation at Break	300	%	ASTM D 638
Flexural Modulus	686.7	MPa	ASTM D 790
Flexural Strength	22.6	MPa	ASTM D 790
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	N	J/m	ASTM D 256
Temperature	-40	°C	-

Other properties	Value	Unit	Test Standard
Density	940	kg/m ³	ASTM D 792

Characteristics

Special Characteristics
High impact or impact modified

Regional Availability
Europe, Asia Pacific

Chemical Resistance
General Chemical Resistance