

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|------------|---------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 4 | g/10min | ASTM D 1238 |
| Temperature | 230 | °C | - |
| Load | 5 | kg | - |

| Mechanical properties | Value | Unit | Test Standard |
|--------------------------------------|-------------|------|---------------|
| ASTM Data | | | |
| Tensile Strength | 24.5 | MPa | ASTM D 638 |
| Elongation at Break | 300 | % | ASTM D 638 |
| Flexural Modulus | 981 | MPa | ASTM D 790 |
| Flexural Strength | 29.4 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | N | J/m | ASTM D 256 |
| Izod Impact notched, Low-Temperature | N | J/m | ASTM D 256 |
| Temperature | -30 | °C | - |

| Other properties | Value | Unit | Test Standard |
|------------------|------------|-------------------|---------------|
| Density | 955 | kg/m ³ | ASTM D 792 |

Characteristics

Special Characteristics
High impact or impact modified

Regional Availability
Europe, Asia Pacific

Chemical Resistance
General Chemical Resistance