

**SLOVASTYR® E BT N**

PET

Plastcom, spol. s r.o.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>15</b>	g/10min	ISO 1133
Temperature	<b>275</b>	°C	-
Load	<b>0.325</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>1600</b>	MPa	ISO 527
Tensile Strength	<b>60</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>1500</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>1</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>260</b>	°C	ISO 11357-1/-3
<b>Other properties</b>			
<b>ISO Data</b>			
Density	<b>1370</b>	kg/m <sup>3</sup>	ISO 1183
Moisture Content	<b>0.1</b>	%	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

Europe