

TRN-8580FH

PET

Teijin Chemicals Ltd.

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	252	°C	ISO 11357-1/-3
Other properties			
Intrinsic Viscosity	0.8	dl/g	-
Color b	0	-	CIE

Characteristics**Processing**

Injection Molding, Sheet Extrusion, Blow Molding

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa