

**TRN-RTJ**

PET

Teijin Chemicals Ltd.

| <b>Thermal properties</b>     | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|-------------------------------|--------------|-------------|----------------------|
| <b>ISO Data</b>               |              |             |                      |
| Melting temperature, 10°C/min | <b>252</b>   | °C          | ISO 11357-1/-3       |
| <b>Other properties</b>       |              |             |                      |
| Intrinsic Viscosity           | <b>0.64</b>  | dl/g        | -                    |
| Color b                       | <b>-2</b>    | -           | CIE                  |

**Characteristics****Processing**

Injection Molding, Fiber Extrusion, Film Extrusion

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa