

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>3</b>	g/10min	ASTM D 1238
Temperature	<b>372</b>	°C	-
Load	<b>5</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Shore D Hardness	<b>60</b>	-	ASTM D 2240
<b>Thermal properties</b>			
<b>ASTM Data</b>			
Melting Temperature	<b>308</b>	°C	ASTM D 3418
<b>Other properties</b>			
Density	<b>2150</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Delivery form**

Powder

**Special Characteristics**

Heat stabilized or stable to heat, Transparent

**Chemical Resistance**

General Chemical Resistance

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa