

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	50	MPa	ISO 527
Stress at break	45	MPa	ISO 527
Strain at break	60	%	ISO 527
Flexural modulus, 23°C	2700	MPa	ISO 178
Izod notched impact strength, +23°C	50	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	25	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Vicat softening temperature, B	107	°C	ISO 306
Burning behav. at 1.5 mm nom. thckn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Yellow Card available	yes	-	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
Yellow Card available	yes	-	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Electric strength	30	kV/mm	IEC 60243-1
Comparative tracking index	250	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1170	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Features

Non Blooming, Thermal Stability

### Special Characteristics

Flame retardant, Halogen-free

### Regional Availability

Europe