

WPC BIO TPS H50-510-35

PLA-W50

Jelu-Werk Josef Ehrler GmbH & Co KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7100	MPa	ISO 527
Tensile Strength	25	MPa	ISO 527
Flexural modulus, 23°C	6150	MPa	ISO 178

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183
Bulk density	550	kg/m ³	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Certifications

Contains renewable resources, Biodegradable, Compostable ISO 13432 (Producer), Compostable ISO 13432 (Certificate)

Regional Availability

Europe