

WPC BIO PLA H60-500-14

PLA-W60

Jelu-Werk Josef Ehrler GmbH & Co KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	4380	MPa	ISO 527
Tensile Strength	26	MPa	ISO 527
Other properties			
Density	1210	kg/m ³	ISO 1183
Bulk density	550	kg/m ³	-

Characteristics**Processing**

Injection Molding

Certifications

Contains renewable resources, Biodegradable

Delivery form

Pellets, Natural Color

Regional Availability

Europe