

**ACRYLITE® L40**

PMMA

Evonik CYRO LLC

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	26	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	3.8	kg	-
Mold Shrinkage, MD	0.0045	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	3200	MPa	ASTM D 638
Tensile Strength	60.7	MPa	ASTM D 638
Elongation at Yield	3	%	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	3000	MPa	ASTM D 790
Flexural Strength	97.9	MPa	ASTM D 790
Rockwell Hardness	M 84	-	ASTM D 785
Izod Impact notched, 1/4 in	19	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Coefficient of Thermal Expansion, MD	72	E-6/K	ASTM D 696
Vicat Temperature	82	°C	ASTM D 1525

Optical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Haze	1	%	ASTM D 1003
Light Transmittance	92	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Water Absorption, Equilibrium	0.3	%	ASTM D 570
Density	1190	kg/m <sup>3</sup>	ASTM D 792
Bulk Density	660	kg/m <sup>3</sup>	-

**Characteristics****Processing**

Injection Molding

**Features**

Amorphous, Light Guiding

**Additives**

Lubricants

**Applications**

Medical

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

North America