

CRYSTALUX® HI532

PMMA

LX MMA Corp.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2.7	g/10min	ISO 1133
Temperature	230	°C	-
Load	3.8	kg	-
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2300	MPa	ISO 527
Stress at break	50	MPa	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Flexural strength	93	MPa	ISO 178
Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA
Rockwell hardness	M 80	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	94	°C	ISO 75-1/-2
Vicat softening temperature, B	102	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
ASTM Data			
Coefficient of Thermal Expansion, MD	70	E-6/K	ASTM D 696

Optical properties	Value	Unit	Test Standard
ISO Data			
Haze	1.5	-	ISO 14782
Luminous transmittance	91	%	ISO 13468-1, -2
Other Standards^{S1}			
Index of Refraction	1.49	-	ISO 489

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1170	kg/m ³	ISO 1183
Water Absorption, 24hr	0.4	%	ASTM D 570

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	70 - 80	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	210 - 240	°C	-
Mold temperature	50 - 70	°C	-

Characteristics**Processing**

Profile Extrusion, Sheet Extrusion

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather, Transparent

Features

Light Guiding

Regional Availability

North America, Europe, Asia Pacific