

**AUROform® H15 black**

POM

Aurora Kunststoffe GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	15	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
Molding shrinkage, normal	1.9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	3000	MPa	ISO 527
Yield stress	65	MPa	ISO 527
Strain at break	30	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	8	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	7	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	176	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

Other properties	Value	Unit	Test Standard
Water absorption	1.3	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	3 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	205	°C	-
Mold temperature	90	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets, Black

**Features**

Homopolymer

**Certifications**

Recycled Resin Content

**Regional Availability**

Europe