

**Product Texts**

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

**Delrin® 100P is a high viscosity acetal homopolymer for use in easy-to-fill molds. Delrin® 100P provides a great combination of toughness and strength, improved processing thermal stability and productivity for injection molding, and low VOC emissions.**

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	2.1	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	2.2	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.9	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Melt Flow Index, MFI	1	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.0195	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.018	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2900	MPa	ISO 527
<sup>[C]</sup> Yield stress	70	MPa	ISO 527
<sup>[C]</sup> Yield strain	26	%	ISO 527
<sup>[C]</sup> Nominal strain at break	45	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1h	2700	MPa	ISO 899-1
<sup>[C]</sup> Tensile creep modulus, 1000h	1500	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	400	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	14	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	13	kJ/m <sup>2</sup>	ISO 179/1eA
<b>ASTM Data</b>			
Tensile Modulus	2940	MPa	ASTM D 638
Tensile Strength	67	MPa	ASTM D 638
Tensile Strength at Yield	67	MPa	ASTM D 638
Elongation at Yield	23	%	ASTM D 638
Elongation at Break	80	%	ASTM D 638
Flexural Modulus	2790	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	120	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	155	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	160	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	110	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-

**Delrin® 100P NC010**

POM

Delrin

<sup>[C]</sup> Burning Behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8</b>	mm	-
Yellow Card available	<b>yes</b>	-	-
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>1.5</b>	mm	-
Coefficient of Thermal Expansion, MD	<b>110</b>	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	<b>110</b>	E-6/K	ASTM D 696
DTUL @ 66 psi	<b>163</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>95</b>	°C	ASTM D 648
Melting Temperature	<b>178</b>	°C	ASTM D 3418

[C]: CAMPUS

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	<b>3.9</b>	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	<b>3.9</b>	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	<b>35</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	<b>55</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	<b>1E12</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>2E13</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>41</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>600</b>	-	IEC 60112
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>16.9</b>	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	<b>0.005</b>	-	ASTM D 150
Dielectric Constant, 1 MHz	<b>3.7</b>	-	ASTM D 150
Surface Resistivity	<b>2E14</b>	Ohm	ASTM D 257
Volume Resistivity	<b>4E14</b>	Ohm*cm	ASTM D 257

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Water absorption	<b>1.4</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.3</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1420</b>	kg/m <sup>3</sup>	ISO 1183
Water Absorption, 24hr	<b>0.4</b>	%	ASTM D 570
Water Absorption, Equilibrium	<b>0.28</b>	%	ASTM D 570
Density	<b>1420</b>	kg/m <sup>3</sup>	ASTM D 792

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding, Film Extrusion, Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion, Wire/Cable Extrusion, Other Extrusion

**Delivery form**

Pellets, Natural Color

**Additives**

Lubricants, Release agent

**Features**

Low Emission, Thermal Stability, Weldable, Homopolymer

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information****Injection molding**

Drying is recommended, but not necessary for newly opened packaging stored in a dry location.

Follow the drying guidelines above in the following cases:

Created: 05.07.2025 Source: www.materialdatacenter.com

Page: 2/3

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.

- If moisture is above the Processing Moisture Content recommendation,
- When a resin container is damaged,
- When the material is not properly stored in a dry place at room temperature, or
- When packaging stays open for a significant time.